

Easy Filler

Product properties

Light, white filler, which is extraordinary easy and practical to apply with its special creamy consistency. Withstands moisture when properly protected by paint or varnish, but is not recommended for areas constantly exposed to water.

- Does not crack
- Excellent sanding properties
- Doesn't sink



Product use

For interior and exterior reparation of cracks, fissures and minor holes in masonry, render, concrete, gypsum, and wood. Prime with priming oil before applying Flügger Easy Filler, when used on wood outdoors.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

Remove loose material and paint by cleaning, sanding and dusting.

Remove dirt, grime, grease and chalking materials by cleaning with Fluren 37.

Water-soluble discolouration, nicotine and soot can be cleaned with Fluren 49.

Sand flat hard, slippery surfaces.

Apply the filler paste and smooth out.

If necessary, sand the surface using a fine-grained abrasive before finishing treatment.

Application

Apply and smooth out using a filler knife.

Apply a sufficient amount and then work and smooth out the filler paste.

Dip the filler knife into water and smoothen afterwards.

Condensation must not occur.

Always perform a test treatment for a check and acceptance of adhesion and result

Expected result

Smooth out surface for additional treatment.

Can be painted with both an aqueous acrylic paint and a solvent-based alkyd paint.

Environmental information

Remove as much filler as possible before cleaning with water. Bring remains of fluent paint to the local recycling centre. Minimize your paint waste by pre-estimating how much paint you need. Keep the leftover paint for future use so you can effectively reduce the environmental impact.

Storage: Cool, frost-free, and tightly closed

Supplementary Info

Registered in the Nordic Ecolabelling Building Products Database for products which can be used in buildings with the Swan label.

Technical Data

Product Type	Plaster & Sealant
Color (plaster)	White
Density (kgs/l)	0.57
m/l, depending on joint width and depth	1
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Recoatable at 20° C, 60 % RH (Hours)	1
Fully cured at 20° C, 60 % RH (Days)	28
Layer thickness (nominal mm)	10
Dilution	Water
Cleaning of Tools etc.	Water

Current TDS Version

February 2023

Replaces TDS Version

December 2021